REPORT DOCUMENTATION PAGE

Form Approved OME No. 0704-0188

Public resorting sursen for this collection of information is estimated to average 1 nour per response, including the time for reviewing instructions, searching existing data sources.

. AGENCY USE ONLY (Leave blank)	2. REPORT DATE	FINAL REPORT 01 May 93 - 30 Apr 97
nni and summi Resonant Tunneling and	Hot Electron Spe	ctroscopy in 5. FUNDING NUMBERS
Buried Rare-Earth Arsen	ide/Semiconducto	r Heterostructures 61102F
<u> </u>		2305/ES
AUTHOR(S)		23037 115
Dr. S. James Allen		
. PERFORMING ORGANIZATION NAM	E(S) AND ADDRESS(ES)	E. PERFORMING ORGANIZATION
University of Californ	REPORT NUMBER	
Quantum Institute		{
Santa Barbara, CA 9310)6	
9. SPONSORING/MONITORING AGENC	Y NAME(S) AND ADORES	S(ES) 10. SPONSORING/MONITORING
United States Air Force		AGENCY REPORT NUMBER
AFOSR/NE		
110 Duncan Ave. Room B	115	F49620-93-1-0329
Bolling AFB DC 20332-	3080	
11. SUPPLEMENTARY HOTES		
		•
122. DISTRIBUTION / AVAILABILITY ST	LTEMENT	12b. DISTRIBUTION CODE
APPROVED FOR PUBLIC REL	EASE: DISTRIBUTI	ON UNLIMITED
13. ABSTRACT (Maximum 200 words)		
A new materials arena has	been opened for quantur	n electron transport devices based on magnetic, semi-
A licw materials atoma mas	1 1 1 1 1 1 1 1 1 1 1 1 1 1 1 1 1 1 1	Epitaxial ultrathin films of a rare earth arsenide, ErAs,
metal compound semicond	uctor neterostructures. I	-P
metal compound semicond were grown in GaAs semic	conductors. The dissimil	arities between the ErAs, a magnetic semimetal, and the
metal compound semicond were grown in GaAs semic compound semiconductor	conductors. The dissimil make possible the fabric	arities between the ErAs, a magnetic semimetal, and the ation of three terminal resonant tunneling transistors
metal compound semicond were grown in GaAs semic compound semiconductor with ultra thin semi-metal	conductors. The dissimil make possible the fabric quantum wells. Resonan	arities between the ErAs, a magnetic semimetal, and the ation of three terminal resonant tunneling transistors at tunneling through semi-metal quantum wells was
metal compound semicond were grown in GaAs semic compound semiconductor with ultra thin semi-metal observed for the first time.	conductors. The dissimil make possible the fabric quantum wells. Resonan A strong coupling of th	arities between the ErAs, a magnetic semimetal, and the sation of three terminal resonant tunneling transistors tunneling through semi-metal quantum wells was e magnetization and the resonant tunneling was
metal compound semicond were grown in GaAs semic compound semiconductor with ultra thin semi-metal observed for the first time.	conductors. The dissimil make possible the fabric quantum wells. Resonan A strong coupling of the tes magnetization control.	arities between the ErAs, a magnetic semimetal, and the sation of three terminal resonant tunneling transistors t tunneling through semi-metal quantum wells was e magnetization and the resonant tunneling was lled resonant tunneling. Nano-composites of ErAs /
metal compound semicond were grown in GaAs semicompound semiconductor with ultra thin semi-metal observed for the first time. discovered that demonstra GaAs were also grown. E	conductors. The dissimil make possible the fabric quantum wells. Resonan A strong coupling of the tes magnetization controllectron transport in these	arities between the ErAs, a magnetic semimetal, and the cation of three terminal resonant tunneling transistors at tunneling through semi-metal quantum wells was e magnetization and the resonant tunneling was led resonant tunneling. Nano-composites of ErAs / systems exhibits giant magneto-resistance,
metal compound semicond were grown in GaAs semic compound semiconductor with ultra thin semi-metal observed for the first time discovered that demonstra GaAs were also grown. Emagnetization controlled in	conductors. The dissimil make possible the fabric quantum wells. Resonan A strong coupling of the magnetization controllectron transport in these sland to island electron h	arities between the ErAs, a magnetic semimetal, and the sation of three terminal resonant tunneling transistors at tunneling through semi-metal quantum wells was e magnetization and the resonant tunneling was alled resonant tunneling. Nano-composites of ErAs / systems exhibits giant magneto-resistance, apping transport. This research program has opened the
metal compound semicond were grown in GaAs semic compound semiconductor with ultra thin semi-metal observed for the first time discovered that demonstra GaAs were also grown. Emagnetization controlled in possibility of high density	conductors. The dissimil make possible the fabric quantum wells. Resonan A strong coupling of the tes magnetization controllectron transport in these sland to island electron to non-volatile information.	arities between the ErAs, a magnetic semimetal, and the cation of three terminal resonant tunneling transistors at tunneling through semi-metal quantum wells was e magnetization and the resonant tunneling was led resonant tunneling. Nano-composites of ErAs / systems exhibits giant magneto-resistance,

14. SUBJECT TERMS			15. NUMBER OF PAGES 6 16. PRICE CODE
17. SECURITY CLASSIFICATION OF REPORT Unclassified	18. SECURITY CLASSIFICATION OF THIS PAGE Unclassified	19. SECURITY CLASSIFICATION OF ABSTRACT Unclassified	20. LIMITATION OF ABSTRACT

NSN 7540-01-280-5500

Final Report

F49620-93-329 "Resonant tunneling and hot electron spectroscopy in buried rare-earth arsenide/semiconductor heterostructures" and

AASERT F49620-93-0440 "Non-linear terahertz electronics with self organized rare-earth arsenide semi-metal/semiconductor composites".

The rare-earth arsenides are magnetic, semimetallic compounds that can be grown epitaxially on III-V compound semiconductors like GaAlAs. These systems open the potential for novel electronics and photonics based on magnetic, semimetal semiconductor heterostructures. The objective of this work was to explore the magnetics, transport and optics and assess the importance of this material system in future magnetics, electronics and photonics.

The technical approach followed several avenues.

- 1. Three terminal resonant tunneling diodes comprised of ErAs quantum wells in AlGaAs heterostructures were successfully grown, fabricated and tested.
- 2. Nano-composites of ErAs islands were successfully grown and used to explore magnetization controlled island island hopping transport.
- 3. ErAs islands were imbedded in highly doped 2-dimensional electron gases to control electron percolation and produce random, self organized quasi-optical Schottky diode arrays for terahertz harmonic generation.
- 4. Near IR photo response of ErAs / GaAs nano-composites was measured to assess the potential for fast fast photo-conductive detectors.

The following milestones and breakthroughs were achieved.

- The contrasting electrical, chemical and structural properties of the ErAs and III-V semiconductors allows ion implant isolation of buried ErAs semimetal from the doped host semiconductor. Followed by contact anneal, selective and specific ohmic contact can be made to ultra thin buried semi-metal layers in semiconductor heterostructures. A simple and effective method fabricating three terminal resonant tunneling diodes follows.
 - Resonant tunneling through semimetal quantum wells was observed for the first time.
- •Using the unique properties of these three terminal resonant tunneling diodes, it was discovered that electrons tunnel through resonant hole channels in the ErAs quantum well resonant tunneling diodes.
 - The dispersion relation of the resonant hole channels was measured.

DTIC QUALITY INSPECTED 5

- A giant spin splitting of the resonant channel was discovered and is understood to be caused by the exchange interaction between the Er 4f spins and the resonant hole channel.
- Following measurements of the hole dispersion we are able to measure the dispersion of the exchange coupling of the Er 4f spins and the resonant holes.
- ErAs islands can be grown with sizes controlled by the growth temperature of the substrate. Superlattices of 2-dimensional sheets ErAs islands can be grown.
- A giant negative magnetoresistance was discovered that points to magnetization controlled hopping conduction between islands.
- Terahertz harmonic generation from self organized Schottky diode arrays has been measured. The predicted enhancement is not observed.
- Preliminary measurements on the near IR photo response indicate that the internal photoemission in ErAs / GaAs nanocomposites may over another route to fast near IR photo detectors

Three terminal resonant tunneling diodes. Ion implantation has little effect on the electrical properties of ultra thin semi-metals. As a result regions of the surrounding III-V semiconductor can be rendered insulating leaving a thin (>0.8nm) protruding metallic sheet. (Fig. 1.) (It was discovered in earlier work that because of the peculiarities of the band structure of ErAs there was no semi-metal semiconductor transition at thicknesses down to 3 monolayers.) Ohmic contact to this sheet leaves a three terminal device in which the control electrode can be as thin as 0.8nm. An abiding materials problem, however, is the




Fig. 1 Ion implantation can render doped regions of the heterostructure insulating without altering the conductivity of ultra-thin buried metal layers.




Fig. 2 The dispersion of the hole channels determined from the thickness dependence of the quantum well potential for resonant tunneling.

quality of the III-V semiconductor grown on top of the rare earth arsenide (ReAs). As a result, while the semi-metal quantum well can be contacted and used to determine the potential in the quantum well, it is difficult to isolate it from the top III-V epilayers. None the less, the semimetal quantum well enables one to define and measure the Fermi energy. This is not possible in conventional III-V heterostructures.




Fig. 3 The resonant channels are distinguished by their dependence on magnetic field.

Two resonant channels were identified and distinguished by there behavior in a magnetic field. Remarkably, a systematic study of the dependence on the quantum well thickness revealed that the resonant channels were hole channels and their dispersion was measured. (Fig. 2)

In modest magnetic fields, a large splitting of the channels was observed which depended on the orientation of the magnetic field. (Fig. 3.) The splitting was measured to be of the order of .1 eV or ~ 1000K. It is caused by the exchange interaction between the 4f spin and the resonant hole states.

By measuring the splitting as a function of the thickness, the dispersion or wave vector dependence of the exchange coupling could be determined. It appears to vanish as k approaches 0. This is expected since the states

at k=0 are predominately on the As and the contact exchange interaction with the 4f spin should be suppressed.

This research points to the possibility of fabricating a device in which the resonant tunneling is controlled by the orientation of the magnetization of a ferromagnetic film.

Growth of ErAs / GaAs nanocomposites. Below 3 monolayers of ErAs the material forms islands. The island size has been found to be determined by the substrate temperature. Around 600 C the islands are of the order of 2 nm, whereas at growth temperatures approaching 700 C the islands are nearing 100 nm. (Fig. 4)

Giant magneto resistance and magnetization controlled island hopping. Resistivity measurements at low temperature in a magnetic field reveal a striking negative magnetoresistance. For some nano-composites the resistance drops some 4 orders of magnitude in a 2




Fig. 4 ErAs island depends on substrate temperature.

Tesla field. (Fig. 5) Theoretical models developed by Petukhov et al. point to size dependent magnetization fluctuation characteristic of nanometer scale paramagnetic particles. The relative orientation determines the hopping rate. More needs to be done establish the mechanism and its dependence on material parameters.

Nano-composites of ErAs / GaAs with doping layers appear like random Schottky diode arrays. Enhanced non-linearity's are expected from two different perspectives. At percolation




Fig. 6 Terahertz third harmonic generation (600 GHz in 1.8 THz out) from a doped layer and a doped layer with ErAs semi-metal islands.

diodes that should be intrinsically non-linear.

Early results are not encouraging. The insertion of the semi-metal islands in an otherwise uniform 2 dimensional electron gas results in lower non-linear response. (Fig. 6).

non-linearity's should be amplified by the strong electric fields that appear at the constrictions. From another perspective we have an array of back to back Schottky




Fig. 5 A giant negative magnetoresistance signals magnetization controlled hopping transport between the islands.

Near IR Photoresponse. Internal photoemission from small ErAs metal particles could lead to fast sensitive near IR photo detectors. They have the same features as does LT GaAs with the As semi-metal cluster replaced by the ErAs. The spectrum of the photo response shows threshold consistent with internal photo-emission from the ErAs particles and that is consistent with the accepted Schottky barrier heights between ErAs and GaAs. Preliminary measurements on the time response find it fast enough to warrant further investigation.

Publications.

Sadwick, L.P., Lee, P.P., Patel, M., Nikols, M., et al. "Epitaxial dysprosium phosphide grown by gas-source and solid-source MBE on gallium arsenide substrates.", J. of Crystal Growth, July 1996, vol.164, (no.1-4):285-90.

Bogaerts, R., Herlach, F., De Keyser, A., Peeters, F.M., et al., "Experimental determination of the Fermi surface of thin Sc_{1-x}Er_xAs epitaxial layers in pulsed magnetic fields.", Phys. Rev. B (Condensed Matter), 15 June 1996, vol.53, (no.23):15951-63.

Brehmer, D.E., Kai Zhang, Schwarz, Ch.J., Chau, S.-P., et al., "Resonant tunneling through rare earth arsenide, semimetal quantum wells.", Solid-State Electronics, June 1996, vol.40, (no.1-8):241-4.

Brehmer, D.E., Kai Zhang, Schwarz, C.J., Chau, S.-P., et al., "Resonant tunneling through ErAs semimetal quantum wells.", Applied Physics Letters, 28 Aug. 1995, vol.67, (no.9):1268-70.

Zhang, K., Brehmer, D.E., Allen, S.J., Jr., Palmstrom, C.J. "Resonant tunneling in semi-metal/semiconductor, ErAs/(Al,Ga)As, heterostructures." <u>Proceedings of the Twenty-First</u>

<u>International Symposium</u>. Edited by: Goronkin, H., Mishra, U. Bristol, UK: IOP Publishing, 1995. p. 845-50.

Brehmer, D.E., Ibbetson, J.P., Kai Zhang, Petukhov, A.G., et al., "Resonant tunneling through (Al,Ga)As/ErAs/(Al,Ga)As, semi-metal quantum wells." <u>Semiconductor Heteroepitaxy. Growth, Characterization and Device Applications</u>, Edited by: Gil, B., Aulombard, R.-L. Singapore: World Scientific,1995. p. 672-5.

Bogaerts, R., De Keyser, A., Herlach, F., Peeters, F.M., et al., "Quantum oscillations in the Hall effect of thin Sc_{1-x}Er_xAs epitaxial layers buried in GaAs." <u>International Conference, High Magnetic Fields in the Physics of Semiconductors</u>. Edited by: Heiman, D. Singapore: World Scientific, 1995. p. 706-9.

Bogaerts, R., De Keyser, A., Herlach, F., Peeters, F.M., et al., "Size effects in the transport properties of thin Sc_{1-x}Er_xAs epitaxial layers buried in GaAs." Solid-State Electronics, April-June 1994, vol.37, (no.4-6):789-92.

Allen, S.J., Brehmer, D., Palmstrom, C.J. "Novel electronics enabled by rare earth arsenides buried in III-V semiconductors.", <u>Rare Earth Doped Semiconductors Symposium</u>, Edited by: Pomrenke, G.S., Klein, P.B., Langer, D.W. Pittsburgh, PA, USA: Mater. Res. Soc, 1993. p. 307-17.

Schmidt, D.R., Ibbetson, J.P., Brehmer, D.E., Palmstrom, C.J. and Allen, S.J., "Giant magnetoresistance of self assembled ErAs islands in GaAs.", to be published Mater. Res. Soc.

Presentations:

Brehmer, D.E., "Resonant tunneling through rare earth arsenide, semimetal quantum wells.", Seventh International Conference on Modulated Semiconductor Structures, Madrid, Spain, 10-14 July 1995.

Brehmer, D.E., "Resonant tunneling in semi-metal/semiconductor, ErAs/(Al,Ga)As, heterostructures.", Twenty-First International Symposium on Compound Semiconductors, San Diego, CA, USA,18-22 Sept. 1994.

Brehmer, D.E., "Resonant tunneling through (Al,Ga)As/ErAs/(Al,Ga)As, semi-metal quantum wells." Semiconductor Heteroepitaxy. Growth, Characterization and Device Applications, Montpellier, France, 4-7 July 1995.

Bogaerts, R. "Quantum oscillations in the Hall effect of thin Sc_{1-x}Er_xAs epitaxial layers buried in GaAs.", 11th International Conference on High Magnetic Fields in Semiconductor Physics, Cambridge, MA, USA, 8-12 Aug. 1994.

Bogaerts, R., "Size effects in the transport properties of thin Sc_{1-x}Er_xAs epitaxial layers buried in GaAs., Sixth International Conference on Modulated Semiconductor Structures, Garmisch-Partenkirchen, Germany, 23-27 Aug. 1993.

Allen, S.J., "Novel electronics enabled by rare earth arsenides buried in III-V semiconductors." Rare Earth Doped Semiconductors Symposium, San Francisco, CA, USA, 13-15 April 1993.

Zhang, K., "Resonant tunneling in semi-metal/semiconductor, ErAs/(Al,Ga)As, heterostructures.", Rare Earth Doped Optoelectronic Materials Workshop, 16-17 June 1994, Hughes Research Lab, Malibu CA.

Personnel participation in this contract:

Name	Position	Current Status
K. Zhang	Post-doctoral researcher	EG&G
SP. Chau	Undergraduate researcher	EG&G
D.E. Brehmer	Graduate student researcher	Writing dissertation
D. Schmidt	Graduate student researcher	Research in progress
S. Rausch	Diploma student, Karlsruhe (without salary support)	Writing Diploma-arbeit
James Ibbetson	Post-doctoral researcher	Continuing
	(without salary support)	
Frank Hegmann	Post-doctoral researcher	University of Alberta
C. Palmstrom	Consultant	Faculty, U. Minnesota